


Snow Lion C2S Coated Art Paper - Gloss

雪狮双面铜版纸

SDPM3, SDPM8



Technical Specifications

| Items | 项目 | Unit | Standard/ Method | Parameters | | | | | | | | | | | | | |
|----------------------------|--------|--------------------|---------------------|------------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| | | | | 80 | 90 | 100 | 105 | 115 | 120 | 128 | 145 | 150 | 152 | 157 | 195 | 200 | 250 |
| Basis Weight | 定量 | gsm | ISO 536 | 80 | 90 | 100 | 105 | 115 | 120 | 128 | 145 | 150 | 152 | 157 | 195 | 200 | 250 |
| Caliper | 厚度 | μm | ISO 534 | 63 | 72 | 79 | 84 | 91 | 95 | 104 | 124 | 124 | 132 | 132 | 176 | 176 | 235 |
| ISO Brightness | 亮度 | % | ISO 2470 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 | 92±1 |
| Bulk | 松厚度 | cm ³ /g | ISO 534 | 0.79 | 0.8 | 0.79 | 0.79 | 0.79 | 0.79 | 0.81 | 0.86 | 0.83 | 0.87 | 0.84 | 0.90 | 0.88 | 0.94 |
| Gloss 75° | 光泽度 | % | ISO 8254/1 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 | ≥63 |
| Ink absorption | 油墨吸收率 | % | K&N | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 | 24±3 |
| Surface Printing Intensity | 表面印刷强度 | m/s | ISO 3783 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 | ≥1.4 |
| Roughness | 粗糙度 | μm | ISO 8791/4 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 | ≤1.20 |

Test conditions: ISO Temperature: 23±1C Humidity: 50±2%RH

* FSC grade is available

* End uses: Magazines, Catalogues, Brochures, Promotional communications, Posters, Leaflets, Flyers